THE FOLLOWING ARE THE ENGLISH TRANSLATION
OF ANNEXES TO THE INTERNATIONAL PRELIMINARY
EXAMINATION REPORT (ARTICLE 34):

Amended Sheets (Pages 24 and 26)

We claim:-

1. Solid pigment preparations comprising as essential constituents

    (A)   from 60% to 85% by weight of at least one organic pigment,

    (B)   from 0.1% to 15% by weight of at least one pigment derivative of the general formula I

$$P \overset{\left[T^1\!-\!B^1\!-\!X \right]_m}{\underset{\left[T^2\!-\!B^2\!-\!Y \right]_n}{<}} \qquad\qquad I$$

where

P   is the residue of the core structure of an organic pigment from the group consisting of quinophthalone and phthalocyanine pigments;

T^1 and T^2 are independently a chemical bond, $-CONR^1-$ or $-SO_2NR^1-$;

B^1 and B^2 are independently a chemical bond, C_1-C_8-alkylene or phenylene;

X and Y   independently represent identical or different groups $-SO_3^-Ka^+$ or $-COO^-Ka^+$;

m and n   are each a rational number from 0 to 3 subject to the proviso that $1 \leq m+n \leq 4$;

Ka^+ is H^+, Li^+, Na^+, K^+, $N^+R^2R^3R^4R^5$ or a mixture thereof;

R^1 is hydrogen; C_1-C_4-alkyl; unsubstituted or C_1-C_{18}-alkyl-substituted phenyl; or unsubstituted or C_1-C_{18}-alkyl-substituted naphthyl;

R^2, R^3, R^4 and R^5 are independently hydrogen; C_1-C_{30}-alkyl; C_3-C_{30}-alkenyl; C_5-C_6-cycloalkyl, unsubstituted or C_1-C_{24}-alkyl-substituted; unsubstituted or C_1-C_{24}-alkyl- or C_2-C_{24}-alkenyl-substituted phenyl; unsubstituted or C_1-C_{24}-alkyl- or C_2-C_{24}-alkenyl-substituted naphthyl; a radical of the formula $-[CHR^6-CHR^7-O]_x-R^8$ where the repeat units $-[CHR^6-CHR^7-O]$ can vary for $x > 1$;

R^6, R^7 and R^8 are independently hydrogen or C_1-C_6-alkyl;

AMENDED SHEET

x   is an integer ≥ 1,

and

(C)   from 14.9% by weight to 39.9% by weight of at least one surface-active additive se-
lected from the group consisting of the nonionic polyethers comprising no primary
amino group, said polyethers' acidic phosphoric, phosphonic, sulfuric and/or sulfo-
nic esters, the salts of these esters and the alkyl- and alkylarylsulfonic acids, their
salts and their condensation products with formaldehyde.

2.   Pigment preparations as claimed in claim 1 in the form of granules having an average
particle size from 50 to 5 000 μm and a BET surface area of ≤ 15 m^2/g.

3.   Pigment preparations as claimed in claim 1 or 2, wherein component (C) is at least one
additive selected from the group consisting of the alkylene oxide copolymers, the reaction
products of alkylene oxides with alcohols, amines, aliphatic carboxylic acids or carbox-
amides, the acidic phosphoric, phosphonic, sulfuric and sulfonic esters of these alkylene
oxide compounds, the salts of these esters and the alkylphenyl- and
alkylnaphthalenesulfonic acids, their salts and their condensation products with formalde-
hyde.

4.   A process for producing pigment preparations as claimed in any of claims 1 to 3, which
comprises wet-comminuting the pigment (A) in aqueous suspension which comprises
some or all of additive (C) and, if desired, some or all of pigment derivative (B) and also, if
desired, prior or subsequent neutralization of the suspension with a base and then drying
the suspension, if necessary after the rest of pigment derivative (B) and additive (C) has
been added.

5.   A process for coloration of macromolecular organic and inorganic materials, which com-
prises incorporating pigment preparations as claimed in any of claims 1 to 3 in these ma-
terials by stirring or shaking.

6.   A process as claimed in claim 5 for coloration of coatings, paints, inks, including printing
inks, and finish systems where the liquid phase comprises water, organic solvents or mix-
tures of water and organic solvents.

7.   A process for coloration of macromolecular organic and inorganic materials using color-
mixing systems, which comprises using pigment preparations as claimed in any of
claims 1 to 3 as mixing components.

AMENDED SHEET

8. A process for coloration of plastics, which comprises incorporating pigment preparations as claimed in any of claims 1 to 3 in the plastics by extruding, rolling, kneading or milling. Solid pigment preparations including pigment derivatives and surface-active additives